Centre for Clean Energy Technology & School of Chemistry and Forensic Science

Faculty of Science

Graphene-based Nanocomposite Materials for High-performance Supercapacitors and Lithium Rechargeable Batteries

A Thesis Presented in Fulfillment of the Requirements for the Degree of

Doctor of Philosophy

By

Bei Wang, B. Sc., M. Eng

University of Technology Sydney

2012

Certificate of Authorship/Originality

I certify that the work in this thesis has not previously been submitted for a degree nor has been submitted as part of requirements for a degree except as fully acknowledged within the text.

I also certify that the thesis has been written by me. Any help that I have received in my research work and the preparation of the thesis itself has been acknowledged. In addition, I certify that all information sources and literature used are indicated in the thesis.

Signature of Student



July 2012

Acknowledgement

First, I would like to express my sincere gratitude to my supervisor, Prof. Guoxiu Wang, who has been guiding and supporting me wholeheartedly through rigorous but fruitful supervision and financial funding for over five years since I started my research career in 2007. Dr. Jane Yao is also greatly acknowledged for all the administrative assistance and lab management, as well as figure processing and enhancement.

Special thanks are given to all my colleagues in the research team at the Centre for Clean Energy Technology for all the valuable discussions, kind co-operation and assistance. It is a pleasure to have worked with all of you and I really appreciate everyone's efforts in creating an intimate atmosphere for the research work.

I am also grateful for the assistance and patience of Rochelle Seneviratne, the Research and Development Officer, Faculty of Science, who always responds to my enquires and sorts out all the administrative issues. Relevant training in the research facilities from Dr. Ronald Shimmon, Dr. Linda Xiao, and all the MAU staff are much appreciated as well. Assoc. Prof. Alison Ung deserves real gratitude for her contribution to reviewing my manuscript and the priceless discussions. I would also like to acknowledge the editorial assistance from Dr. Fiona MacIver for proofreading this thesis.

Deep gratitude is to be expressed to my wife, my parents and my relatives, who have been caring and sustaining me over these years. Without your continuous support, I could not have finalized my PhD study and become a mature and responsible person. My upcoming baby fills me with joy. This thesis is also for you, my son. Thank you for bringing luck and happiness to me and to our family.

Table of Contents

List of Schemes, Tables and Figures

Schemes

Tables

Figures

Fig. 5-3 TEM images of the as-prepared Mn_3O_4/GNS nanocomposites: (a) a low magnification TEM image showing dense Mn_3O_4 nanoparticles deposited on a large area of graphene nanosheets and the SAED pattern (inset) displaying graphene (0 0 2) and Mn_3O_4 (1 0 3), (2 1 1), and (2 2 0) diffraction rings; (b) an HRTEM image illustrating the *d*-spacing of Mn_3O_4 nanoparticles, which were evaluated to be around 10 nm in size.

Fig. 5-4 AFM images of the as-prepared Mn_3O_4/GNS nanocomposites: (top) an image taken in a scan area of 500 nm by 500 nm, displaying graphene nanosheets (indicated by arrows) with embedded Mn_3O_4 nanoparticles (indicated by circles); (bottom) height profile across the examined area, as indicated by the red line, from which the particle size was determined to be 9.7 nm and 12.6 nm for particles (a) and (b), respectively.

Fig. 5-5 CV curves of dried graphene nanosheets at a 5 mV s^{-1} scan rate in (a) 1 M Na_2SO_4 and (b) 6 M KOH, and CV curves of Mn_3O_4/GNS nanocomposite powders at scan rates of 5 mV s^{-1}, 10 mV s^{-1}, 20 mV s^{-1}, and 50 mV s^{-1} in (c) 1 M Na_2SO_4 and (d) 6 M KOH.

Fig. 6-1 (a) XRD pattern and (b) Raman spectrum of the as-prepared Co_3O_4/GNS nanocomposite material.

Fig. 6-2 (a) XRD and (b) Raman spectrum of pure graphene nanosheets.

Fig. 6-3 FE-SEM images of the Co_3O_4/GNS nanocomposite obtained under GB-HR mode: (a) numerous curly graphene nanosheets observed at a low magnification, and (b) a higher magnification image, displaying the distribution of Co_3O_4 nanoparticles on graphene nanosheets. The embedded Co_3O_4 nanoparticles are ~20 nm in size.

Fig. 9-10 Cycling performances of CoS_2/GNS, GNS and CoS_2 nanoparticles at 0.5 A g^{-1} and 1 A g^{-1}, respectively in 1 M $LiClO_4$ in PC for 1500 cycles.

Abstract

Human activity and energy supplies mainly rely on the consumption of non-regenerative fossil fuels. With the gradual decrease of these carbon-based energy sources and the increase in environmental pollution, finding alternative green and sustainable energies has become critical. Therefore, innovative and renewable energy technologies must be developed to combat global warming and climate change.[1, 2] Extensive research has been performed on the development of solar cells,[3, 4] fuel cells,[5] lithium-ion batteries[6, 7] and supercapacitors[8, 9] to replace carbon-based energy.

Graphene has been considered a promising electrode material for energy storage applications due to its ultrahigh surface area (2600 m^2 g^{-1}),[10] excellent electric conductivity,[11] and one-atom thick two-dimensional sp^2 carbon arrangement.[12] However, the surface area of graphene nanosheets (GNS) is often dramatically reduced because monolayer GNS always stack to multilayer in the dry state. The stacking of GNS leads to unexposed surface area, which hinders the ion diffusion from the electrolyte to the electrode, resulting in a low electrochemical performance.

To prevent the re-stacking of GNS, and thus maintain well-exposed surface area, nanocrystals can be inserted between graphene layers to form nanocomposite materials. With the above motivation, graphene-based nanocomposite materials have been intensively studied in this thesis. All the materials examined were prepared via different synthesis techniques and well characterized. Their electrochemical properties were evaluated for supercapacitors and/or lithium rechargeable batteries. Sn/GNS is shown to have a very high reversible specific capacity of 785 mAh g^{-1}. Mn_3O_4/GNS shows a specific capacitance of 256 F g^{-1}, almost double that of pure GNS. Of the examined materials, Co_3O_4/GNS presents the highest supercapacitance of 478 F g^{-1} and a rechargeable specific capacity of 722 mAh g^{-1}. S/GNS generates ultra-high specific capacity of up to 1580 mAh g^{-1} and excellent rate capability. SnO_2 nanoparticles supported by GNS deliver a specific capacity of 830 mAh g^{-1} with well maintained cycling stability. CoS_2/GNS yields high capacitances of 314 F g^{-1} in an aqueous electrolyte and 141 F g^{-1} in an organic electrolyte. The enhanced overall electrochemical performances of these nanocomposite materials can be attributed to the dual contributions of the decorating materials, creating enlarged interlayer spacing, and graphene itself, with its facility for flexible nanolayered structure. The results of this study of these graphene-based nanocomposite materials indicate their great potential for application to practical energy storage devices.